

SUPERIOR 150HS

E31

VERSION: 160727 Page: 1/2

2K HS ACRYLIC POLYURETHANE CLEAR COAT

DEFINITION

SUPERIOR 150HS is a High Solid very easy to apply acrylic polyurethane clear coat for car refinishing. After application, it acts as a very fast-drying clear coat and a high-gloss is reached. It is applied directly over the base layer 15 - 20 minutes after solvent evaporation. It is recommended to apply a light first coat followed by two further coats in criss-cross pattern. It is important to allow time for evaporation between coats. It may be diluted up to 25% of thinner by increasing its yield. It may be also very easily sanded as well as polished to eliminate possible imperfections.

PHYSICAL CHARACTERISTICS

Nature: Acrylic 2K
Colour: Colourless
Specific weight: 1,0 kg/l at 20°C
Viscosity CF/4: 20" at 20°C

Dry film thickness: 50-60 microns 2 coats

Yield: 9-10 m^2/l

Solids content: 53 % Superior 150HS

45 % Application (100:50:10 vol)

42 % Application (100:50:25 vol) **VOC:** 489 g/l Application (100:50:10 vol)

519 g/l Application (100:50:25 vol)

AUXILIARY PRODUCTS

P4000 Slow Hardener S322 Standard thinner P5000 Standard Hardener S324 Slow thinner

P6000 Fast Hardener P7000 Extra-fast Hardener

		•	•
T ^e (℃)	Hardener	Hardener	Thinner Optional
< 18	P6000 -P7000	P6000	S322
18 - 25	P5000-P6000	P5000	S322
> 25	P5000	P4000	S324

VERSION: 160727 Page: 2/3

SURFACE PREPARATION

A 15 - 20 minutes flash off is required between the basecoat and the **SUPERIOR 150HS** application.

MIXING RATIO

Superior 150HS	A B C		S	⊕ MB
			20°C	
P4000				5h
P5000	100:50:10-25 volume	2:1	20" F/4	5h
P6000				2,5h
P7000				2 h

APPLICATION METHOD

	mm	bar	cm cm	ST.	<u>/</u> †/†/
> 11/2	1,3-1,5	3-3,5	15-20		
***************************************	1,3-1,8	3-3,5	15-20	2-3	5'-10'
NVLP	1,3-1,5	3-3,5	10		

DRYING TIMES

20° C

60º C

Short wave IR

	<u> </u>	R		9	
P4000	20'	3h	5h	8h	12h
P5000	15'	3h	5h	7h	12h
P6000	15'	2,5h	4h	6h	9h
P7000	10'	2h	3h	6h	8h

P4000	35'
P5000	25'
P6000	
P7000	

	FLASH OFF	FULL BAKE
LIGHT	5'	10'
DARK	4'	8'
METALLIC	5'	10'

SUPERIOR 150HS

\mathbb{B}

2K HS ACRYLIC POLYURETHANE CLEAR COAT

VERSION: 160727 Page: 3/3

REMARKS

Humidity affects clear coat components so the application equipment should be absolutely dry.

Close the hardener container immediately after use.

Do not use when relative humidity is higher than 70%.

Do not use at temperatures lower than +10°C. In this case dry in spray booth.

EQUIPMENT CLEANING

Use a cleaning thinner before the pot life has expired.

SAFETY

Follow instructions of product label. For more information check the Safety Data Sheet. Compliant with the National Statutory Regulation for Health and Safety at Work and Waste Disposal.

STORAGE

Store the product in a ventilated place far from direct exposure to sunlight. Keep between $+5^{\circ}$ C and $+30^{\circ}$ C.

GUARANTEE

In unopened original packaging, one year from manufacturing date.

For any technical information contact with our Customer Attention Service or our Technical Department. ROBERLO SA declines any responsibility due to an incorrect use of the product.