


F0901 UNIVERSAL POLYESTER PUTTY

VERSION: 121212

DEFINITION Polyester putty for bodywork. Formulated to enable fast repairs, it has excellent adhesion to metal and a high filling power that allows it to level large defects. Its thixotropy ensures an easy application to awkward areas. PHYSICAL CHARACTERISTICS Nature: Unsaturated polyester Colour: Cream Specific weight: 1,9 kg/l at 20°C 50 g/1VOC: **Mixing Application** AUXILIARY PRODUCTS Hardener PBO SUITABLE SURFACES It may be applied on steel and polyester surfaces. When maximum protection is required apply on epoxy primer. Do not apply on thermoplastic finishes and Wash Primers. SURFACE PREPARATION 1 - Identify surface. 2 - Process: Polyester PROCESS Steel **UP-GFK P80** √ $\sqrt{}$ P150 √ $\sqrt{}$ Cleaning √ $\sqrt{}$ thinner

UAB "SVYDIS" Palemono str.171, Kaunas, Lithuania Tel.: +370-37-341739: Fax.: +370-37-341744: www.svvdis.com



1 – APPLICATION

2 – SANDING

	U: U	2>+ 100		A V		-			ORBIT		
10°C	100:2	6,5'	30'		TIME		INITIAL		7 - 5 mm	P120	P80
10 0					5 min						100
		5'	20'		DISTAN CE						
20°C					80 cm						P150
30°C		3,5'	15'		MAX. T		FINAL	V	5 - 3 mm	P220	P240
					80°C						1 - 10

REMARKS

Do not add more hardener than specified. Mix thoroughly. It must be isolated before applying finish coating. Polyester putties will not harden at temperatures under +5°C.

EQUIPMENT CLEANING

Clean putty knifes with a cleaning thinner before the product hardens.

SAFETY

Follow instructions of product label. For more information check the Safety Data Sheets. Compliant with the National Statutory Regulation for Health and Safety at Work and Waste Disposal.

one year

from

STORAGE

GUARANTEE

In

Store the product in a ventilated place far from direct exposure to sunlight. Keep between +5°C and +30°C.

SUGGESTION:

Dry sanding on polyester putties is always recommended because the dampness retained in the putty during wet sanding might cause problems in the support as well as in the finishing.

For any technical information contact with our Customer Attention Service or our Technical Department. UAB Svydis declines any responsibility due to an incorrect use of the product.

manufacturing date.

unopened original packaging,

UAB "SVYDIS" Palemono str.171, Kaunas, Lithuania Tel.: +370-37-341739; Fax.: +370-37-341744; www.svydis.com