F0902 FIBER PUTTY

VERSION: 121212

DEFINITION

Polyester putty reinforced with fibreglass to increase its resistance. Appropriate to repair such composites as polyester pieces and rusted metallic areas. The small size of the fibre particles, 6 mm, ensures easy spreading.

PHYSICAL CHARACTERISTICS

Nature: Unsaturated polyester

Colour: Grey

Specific weight: $1,6 \text{ kg/l at } 20^{\circ}\text{C}$

VOC: 37 g/l Mixing Application

AUXILIARY PRODUCTS

Hardener PBO

SUITABLE SURFACES

It may be applied on steel or polyester. When maximum protection is required apply on epoxy primer. Do not apply on thermoplastic finishes and Wash Primers.

SURFACE PREPARATION

- 1 Identify surface.
- 2 Process:

PROCESS		Steel	Polyester UP-GFK	
5	P80		4	4
	P150		1	1
	Cleaning thinner	Ţ	1	1



F0902 FIBER PUTTY

1 - APPLICATION

2 - SANDING

	: : WEIGHT	2>+		1 1 1		INITIAL		REVOLU TIONS	
10°C		8'	30'		TIME 5 min			800 rpm	P80
20°C	100:2	6'	20'		DISTAN CE 80 cm	FINAL		ORBIT	
30°C		4'	15'	10.	TMAX. 80°C		ł	7 - 5 mm	P150

REMARKS

It must be isolated with a polyester putty before applying primer. Do not add more hardener than specified. Mix thoroughly. Polyester putties will not harden at temperatures under +5°C.

EQUIPMENT CLEANING

Clean putty knifes with a cleaning thinner before the product hardens.

SAFETY

Follow instructions of product label. For more information check the Safety Data Sheets. Compliant with the National Statutory Regulation for Health and Safety at Work and Waste Disposal.

STORAGE

Store the product in a ventilated place far from direct exposure to sunlight. Keep between +5°C and +30°C.

GUARANTEE

In unopened original packaging, one year from manufacturing date.

For any technical information contact with our Customer Attention Service or our Technical Department.

UAB Svydis declines any responsibility due to an incorrect use of the product.

SUGGESTION:

Due to the hardness of NORDFLEX F0902 FIBER PUTTY for ease of application begin sanding before product has completely hardened.